

GICA INDJAZAT - CEM I 52,5 N

Technical data:

Chemical analyses

Sulphate content (SO ₃)	< 2.5 %
Chloride content (Cl)	< 0.1 %
Teneur in (MgO)	< 1 %
Loss on Fire (PAF)	0,5–1,5 %

Mineralogical composition of clinker (BUG)

C3S	≥ 60 %
C3A	3 – 7,5 %

Physical properties

Normal consistency	26 to 28 %
Time to start taking	≥ 45 min
End of take	150 to 230 min
Expansion	< 5mm
Finesse (SSB)	3200-3800 (cm ² /g)

Compressive strength


2 days (EN 196-1)	≥ 20 Mpa
28 days (EN196-1)	≥ 52.5 MPa

GICA INDJAZAT



Dosages:

Except for specific composition; Average dosage for common concrete:



Safety instructions:

- Avoid contact with skin and eyes
- Use appropriate equipment: gloves, waterproof shoes, glasses.
- Do not inhale dust.

